

LP347透過率

波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)
1500	56.86	1240	72.64	980	98.66	720	96.57	460	84.66
1490	56.96	1230	73.93	970	98.83	710	93.90	450	93.80
1480	57.05	1220	75.26	960	98.89	700	90.39	440	89.09
1470	57.20	1210	76.57	950	98.97	690	85.59	430	70.87
1460	57.35	1200	77.93	940	99.01	680	80.09	420	55.09
1450	57.56	1190	79.29	930	99.04	670	73.45	410	48.87
1440	57.81	1180	80.67	920	99.09	660	67.68	400	54.01
1430	58.10	1170	82.09	910	99.02	650	61.56	390	72.94
1420	58.45	1160	83.49	900	98.97	640	56.26	380	83.15
1410	58.80	1150	84.90	890	99.03	630	51.92	370	53.24
1400	59.27	1140	86.30	880	99.05	620	48.54	360	29.31
1390	59.72	1130	87.64	870	98.97	610	46.40	350	21.78
1380	60.29	1120	88.96	860	98.96	600	45.52	340	24.15
1370	60.85	1110	90.23	850	98.97	590	46.12	330	39.42
1360	61.38	1100	91.37	840	98.77	580	48.53	320	59.42
1350	62.12	1090	92.47	830	98.61	570	53.31	310	52.24
1340	62.88	1080	93.43	820	98.66	560	60.67	300	27.16
1330	63.68	1070	94.34	810	98.63	550	71.14	290	8.19
1320	64.46	1060	95.15	800	98.72	540	83.37	280	1.41
1310	65.29	1050	95.87	790	98.61	530	94.05	270	0.07
1300	66.25	1040	96.52	780	99.23	520	96.98	260	0.00
1290	67.22	1030	97.07	770	99.21	510	91.03	250	0.00
1280	68.20	1020	97.57	760	99.34	500	81.32	240	0.00
1270	69.22	1010	97.94	750	99.26	490	73.85	230	0.00
1260	70.28	1000	98.24	740	99.06	480	71.55	220	0.01
1250	71.39	990	98.50	730	98.22	470	75.57	210	0.01
								200	0.00