

LP389透過率

波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)
1500	63.70	1240	85.99	980	97.65	720	97.78	460	98.59
1490	64.15	1230	87.09	970	97.67	710	97.80	450	98.99
1480	64.59	1220	88.12	960	97.55	700	97.90	440	98.70
1470	65.03	1210	89.11	950	97.52	690	97.93	430	97.03
1460	65.59	1200	90.05	940	97.47	680	97.99	420	95.25
1450	66.15	1190	91.00	930	97.55	670	98.09	410	94.20
1440	66.76	1180	91.86	920	97.49	660	98.15	400	94.80
1430	67.46	1170	92.68	910	97.40	650	98.02	390	61.48
1420	68.16	1160	93.43	900	97.57	640	97.87	380	6.38
1410	68.92	1150	94.14	890	97.56	630	97.88	370	0.20
1400	69.73	1140	94.79	880	97.71	620	97.63	360	0.01
1390	70.61	1130	95.39	870	97.82	610	97.54	350	0.00
1380	71.53	1120	95.91	860	97.82	600	97.27	340	0.00
1370	72.41	1110	96.34	850	97.78	590	97.42	330	-0.00
1360	73.26	1100	96.73	840	97.93	580	97.45	320	0.00
1350	74.37	1090	97.06	830	98.20	570	97.56	310	0.00
1340	75.39	1080	97.28	820	98.13	560	97.67	300	0.00
1330	76.46	1070	97.51	810	98.15	550	97.63	290	0.00
1320	77.48	1060	97.62	800	98.10	540	97.50	280	0.00
1310	78.47	1050	97.72	790	98.05	530	97.25	270	0.00
1300	79.58	1040	97.80	780	98.01	520	97.19	260	0.00
1290	80.68	1030	97.79	770	98.01	510	97.41	250	0.00
1280	81.73	1020	97.86	760	97.94	500	97.94	240	-0.00
1270	82.74	1010	97.83	750	97.87	490	98.31	230	0.00
1260	83.81	1000	97.76	740	97.88	480	98.50	220	0.00
1250	84.87	990	97.72	730	97.87	470	98.44	210	0.01
								200	0.00