

LP800透過率

波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)
1100	95.80	950	98.99	800	40.76	650	0.00	500	0.00
1090	96.13	940	99.14	790	16.60	640	0.00	490	0.00
1080	96.33	930	99.29	780	4.35	630	0.00	480	0.00
1070	96.63	920	99.27	770	0.86	620	0.00	470	0.00
1060	96.89	910	99.48	760	0.11	610	0.00	460	0.00
1050	97.14	900	99.37	750	0.01	600	0.00	450	0.00
1040	97.39	890	99.52	740	0.00	590	0.00	440	-0.01
1030	97.62	880	99.37	730	0.00	580	0.00	430	0.00
1020	97.84	870	99.06	720	0.00	570	0.00	420	-0.01
1010	98.03	860	98.98	710	0.00	560	0.00	410	-0.01
1000	98.24	850	97.85	700	0.00	550	0.00	400	0.00
990	98.44	840	95.89	690	0.00	540	0.00	390	0.00
980	98.64	830	91.98	680	0.00	530	0.00	380	0.00
970	98.81	820	82.55	670	0.00	520	0.00	370	0.00
960	98.92	810	65.23	660	0.00	510	0.00	360	0.00
								350	0.00