

LP830透過率

波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)
1100	96.29	950	99.18	800	3.24	650	0.00	500	0.00
1090	96.51	940	99.26	790	0.62	640	0.00	490	0.00
1080	96.77	930	99.31	780	0.11	630	0.00	480	0.00
1070	97.01	920	99.47	770	0.02	620	0.00	470	0.00
1060	97.26	910	99.32	760	0.01	610	0.00	460	0.00
1050	97.51	900	99.23	750	0.00	600	0.00	450	0.00
1040	97.70	890	98.94	740	0.00	590	0.00	440	0.00
1030	97.90	880	98.69	730	0.00	580	0.00	430	0.00
1020	98.09	870	97.33	720	0.00	570	0.00	420	0.00
1010	98.30	860	94.79	710	0.00	560	0.00	410	0.00
1000	98.47	850	89.30	700	0.00	550	0.00	400	0.00
990	98.68	840	78.63	690	0.00	540	0.00	390	0.00
980	98.83	830	59.49	680	0.00	530	0.00	380	0.00
970	98.95	820	32.84	670	0.00	520	0.00	370	0.00
960	99.14	810	12.26	660	0.00	510	0.00	360	0.00
								350	0.01