

LP695透過率

波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)	波長 (nm)	透過率 (%)
1100	95.19	950	98.11	800	98.55	650	1.29	500	0.00
1090	95.51	940	98.28	790	98.49	640	0.82	490	-0.01
1080	95.75	930	98.34	780	98.17	630	0.54	480	0.00
1070	96.00	920	98.35	770	98.19	620	0.36	470	0.00
1060	96.25	910	98.40	760	98.00	610	0.25	460	0.01
1050	96.46	900	98.42	750	97.28	600	0.17	450	0.00
1040	96.71	890	98.44	740	96.34	590	0.11	440	0.00
1030	96.91	880	98.42	730	93.97	580	0.07	430	0.00
1020	97.06	870	98.20	720	88.21	570	0.04	420	0.00
1010	97.28	860	98.55	710	76.37	560	0.01	410	0.00
1000	97.45	850	98.25	700	55.05	550	0.01	400	0.00
990	97.63	840	98.59	690	28.99	540	0.00	390	0.00
980	97.74	830	98.50	680	11.57	530	0.00	380	0.00
970	97.86	820	98.37	670	4.36	520	0.00	370	0.00
960	97.96	810	98.35	660	2.24	510	0.00	360	0.00
								350	0.01